CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CEMENT/2015-16 Date: 23.10.2015

TEST REPORT ON CEMENT

* CUSTOMER	:	**Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.
*AGENCY	:	**Technical Manager (West),** KRIDL, PIU, Bangalore.
*NAME OF THE WORK	:	Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.
REFERENCE	:	AEE/SSD/PR/101/2015-16 Dated: 21.10.2015
SAMPLE ID	:	Cement
SAMPLE RECEIVED ON	:	21.10.2015
PERIOD OF TESTING	:	21.10.2015 to 23.10.2015

CIVIL ENGINEERING TESTING LABORATORY www.civiltechconsultants.com

The results of the tests conducted on the cement sample are as follows:

Sl. No	Descriptions	Test Method as per IS	Test Result	Requirements as per IS: 8112-2013
1	Standard Consistency	IS-4031 (Part -4) 1988(RA-2009)	30.00 %	-
2	a) Initial Setting Time	IS-4031 (Part -5) 1988(RA-2009)	160 Minutes	Not Less than 30 Minutes
	b) Final Setting Time	IS-4031 (Part -5) 1988(RA-2009)	485 Minutes	Not More than 600 Minutes
3	Soundness by Le Chartlier Method	IS-4031 (Part-3) 1988(RA-2009)	1 mm	Not more than 10mm

*Information is furnished by the Customer/Representative.

Civil-Tech Consultants & Engineers Bangalore

Note:

⇒ The report shall not be reproduced, except in full, without the written approval of the laboratory.

⇒ The results indicated above are based on the tests carried out on the samples received in the laboratory.

⇒ Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

AE-12
23/10
ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ. ರಸ್ತೆ, ರಾಜಾಜಿನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/SAND-Gradation/2015-16 : 23.10.2015

TEST REPORT ON DETERMINATION GRADATION OF FINE AGGREGATES

*** Customer** : **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.

*** Agency** : **Technical Manager (West),** KRIDL, PIU, Bangalore.

*** Name of Work** : Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.

Reference : AEE/SSD/PR/101/2015-16 Dated: 21.10.2015

Technical Reference : IS : 2386 Part 1 - 1963 RA-2007

Sample ID : Fine Aggregates

Sample Received on : 21.10.2015

Date of Testing : 23.10.2015

Total Wt. of Aggregates in gms **1000**

Is Sieve Size in mm	Cumulative Weight Passing in %	Spec.Limits as per IS 383-1970 (RA- 2007)			
		Zone-I	Zone-II	Zone-III	Zone-IV
10	100	100	100	100	100
4.75	93.30	90-100	90-100	90-100	95-100
2.36	77.80	60-95	75-100	85-100	95-100
1.18	59.10	30-70	55-90	75-100	90-100
600 Micron	38.90	15-34	35-59	60-79	80-100
300 Micron	13.20	5-20	8-30	12-40	15-50
150 Micron	2.90	0-10	0-10	0-10	0-15

* Information is furnished by the Customer/Representative

Remarks : This sample is under Zone-II specific limits.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

AE-12

23/10

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು
ಎಸ್.ಎಂ ರಸ್ತೆ, ರಾಜಾಜಿನಗರ

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/AGG/GR/2015-16 : 23.10.2015

TEST REPORT ON COARSE AGGREGATES

*** Customer** : **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.

*** Agency** : **Technical Manager (West),** KRIDL, PIU, Bangalore.

*** Name of Work** : Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.

Reference : AEE/SSD/PR/101/2015-16 Dated: 21.10.2015

Technical Reference : IS : 2386 Part 1 -1963 RA-2007

Sample ID : Coarse Aggregates (40mm)

Sample Received on : 21.10.2015

Date of Testing : 23.10.2015

Total Wt. of Aggregates in gms= **10000**

Is Sieve Size in mm	Cumulative Weight Passing in %	Spec.Limits as per IS 383-1970 (RA- 2007)	
		Graded	Single Sized
80	100	100	-
63	100	-	100
40	97.14	95-100	85-100
20	43.02	30-70	0-20
10	13.86	10-35	0-5
4.75	2.02	0-5	-

* Information is furnished by the Customer/Representative

Remarks : This sample is under Graded specific limits.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

KE-12

23/10

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ
ಎಸ್.ಎಂ ರಸ್ತೆ, ರವೀಂದ್ರ

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/AGG/GR/2015-16 : 27.10.2015

TEST REPORT ON COARSE AGGREGATES

*** Customer** : **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.

*** Agency** : **Technical Manager (West),** KRIDL, PIU, Bangalore.

*** Name of Work** : Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.

Reference : AEE/SSD/PR/101/2015-16 Dated: 21.10.2015

Technical Reference : IS : 2386 Part 1 -1963 RA-2007

Sample ID : Coarse Aggregates (40mm)

Sample Received on : 24.10.2015

Date of Testing : 27.10.2015

Total Wt. of Aggregates in gms= **10000**

Is Sieve Size in mm	Cumulative Weight Passing in %	Spec.Limits as per IS 383-1970 (RA- 2007)	
		Graded	Single Sized
80	100	100	-
63	100	-	100
40	97.32	95-100	85-100
20	42.53	30-70	0-20
10	11.69	10-35	0-5
4.75	1.16	0-5	-

* Information is furnished by the Customer/Representative

Remarks : This sample is under Graded specific limits.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

AE-12

27/10

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು
ಎಸ್.ಎಂ ರಸ್ತೆ, ಮಲ್ಲೇಶ್ವರಂ

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 10.11.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

***Customer**	: **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.
***Agency**	: **Technical Manager (West),** KRIDL, PIU, Bangalore.
***Name of the work**	: Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.
***Reference**	: AEE/SSD/PR/101/2015-16 Dated: 21.10.2015
***Sample ID**	: Road Concrete
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
***Grade of Concrete**	: M_{20}
Compressive Strength as on	: 7^{th} day
Sample Received on	: 10.11.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	03.11.2015	10.11.2015	8.115	355.6	15.80
2	03.11.2015	10.11.2015	8.137	365.7	16.25
3	03.11.2015	10.11.2015	8.187	379.8	16.88

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ ಕೃಷ್ಣ, ಕಾವೇರಿನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 01.12.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

*Customer	: **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.
*Agency	: **Technical Manager (West),** KRIDL, PIU, Bangalore.
*Name of the work	: Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.
*Reference	: AEE/SSD/PR/101/2015-16 Dated: 21.10.2015
*Sample ID	: Road Concrete
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
*Grade of Concrete	: M_{20}
Compressive Strength as on	: 28^{th} day
Sample Received on	: 01.12.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	03.11.2015	01.12.2015	8.215	478.9	21.28
2	03.11.2015	01.12.2015	8.326	489.6	21.76
3	03.11.2015	01.12.2015	8.287	501.7	22.30

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

AE-12

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ ರಸ್ತೆ, ಪದ್ಮನಾಭನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 12.11.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

***Customer**	: **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.
***Agency**	: **Technical Manager (West),** KRIDL, PIU, Bangalore.
***Name of the work**	: Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.
***Reference**	: AEE/SSD/PR/101/2015-16 Dated: 21.10.2015
***Sample ID**	: Road Concrete
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
***Grade of Concrete**	: M_{20}
Compressive Strength as on	: 7^{th} day
Sample Received on	: 12.11.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	05.11.2015	12.11.2015	8.138	364.5	16.20
2	05.11.2015	12.11.2015	8.164	378.2	16.81
3	05.11.2015	12.11.2015	8.215	389.7	17.32

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

AE-12

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ. ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 03.12.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

*Customer	: **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.
*Agency	: **Technical Manager (West),** KRIDL, PIU, Bangalore.
*Name of the work	: Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.
*Reference	: AEE/SSD/PR/101/2015-16 Dated: 21.10.2015
*Sample ID	: Road Concrete
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
*Grade of Concrete	: M_{20}
Compressive Strength as on	: 28^{th} day
Sample Received on	: 03.12.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	05.11.2015	03.12.2015	8.193	477.2	21.21
2	05.11.2015	03.12.2015	8.312	515.7	22.92
3	05.11.2015	03.12.2015	8.274	494.5	21.98

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

06-12

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎ.ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 14.11.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

*Customer : **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.

*Agency : **Technical Manager (West),** KRIDL, PIU, Bangalore.

*Name of the work : Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.

*Reference : AEE/SSD/PR/101/2015-16 Dated: 21.10.2015

*Sample ID : Road Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

*Grade of Concrete : M_{20}

Compressive Strength as on : 7^{th} day

Sample Received on : 14.11.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	07.11.2015	14.11.2015	8.125	363.2	16.14
2	07.11.2015	14.11.2015	8.211	389.4	17.31
3	07.11.2015	14.11.2015	8.169	374.5	16.64

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

AE-12

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 05.12.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

*Customer : **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.

*Agency : **Technical Manager (West),** KRIDL, PIU, Bangalore.

*Name of the work : Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.

*Reference : AEE/SSD/PR/101/2015-16 Dated: 21.10.2015

*Sample ID : Road Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

*Grade of Concrete : M_{20}

Compressive Strength as on : 28^{th} day

Sample Received on : 05.12.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	07.11.2015	05.12.2015	8.427	489.3	21.75
2	07.11.2015	05.12.2015	8.353	477.8	21.24
3	07.11.2015	05.12.2015	8.218	471.7	20.96

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ನಗರಪಾಲಿಕೆ
ಎಸ್.ಎಂ. ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 17.11.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

*Customer : **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.

*Agency : **Technical Manager (West),** KRIDL, PIU, Bangalore.

*Name of the work : Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.

*Reference : AEE/SSD/PR/101/2015-16 Dated: 21.10.2015

*Sample ID : Road Concrete

Size of cubes : 150mmx150mmx150mm

Cross Sectional Area : 22500 mm^2

Technical Reference : IS: 516-1959 (Reaffirmed 2008)

*Grade of Concrete : M_{20}

Compressive Strength as on : 7^{th} day

Sample Received on : 17.11.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	10.11.2015	17.11.2015	8.125	370.6	16.47
2	10.11.2015	17.11.2015	8.169	394.5	17.53
3	10.11.2015	17.11.2015	8.235	381.6	16.96

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

AE-12

ಸಹಾಯಕ ಕಾರ್ಯಪಾಲಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು [illegible]

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ja@civiltechconsultants.com / info@civiltechconsultants.com

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

NABL - Accredited Laboratory as per ISO / IEC-17025 :2005

T-2377

Job No.: CTCE/BBMP/W.No.12/KRIDL/CSR-10/979d/CUBE/2015-16 08.12.2015

TEST REPORT ON COMPRESSIVE STRENGTH OF CONCRETE CUBES

*Customer	: **Asst. Executive Engineer,** Shettyhalli Sub Division, BBMP, Bangalore.
*Agency	: **Technical Manager (West),** KRIDL, PIU, Bangalore.
*Name of the work	: Improvements to roads and drains at Narayanareddy Layout at Abbigere in Ward No. 12 of Shettyhalli Sub Division, BBMP, Bangalore.
*Reference	: AEE/SSD/PR/101/2015-16 Dated: 21.10.2015
*Sample ID	: Road Concrete
Size of cubes	: 150mmx150mmx150mm
Cross Sectional Area	: 22500 mm^2
Technical Reference	: IS: 516-1959 (Reaffirmed 2008)
*Grade of Concrete	: M_{20}
Compressive Strength as on	: 28^{th} day
Sample Received on	: 08.12.2015

Sl.No.	Date of casting	Date of testing	Weight of cube (Kg)	Failure load (KN)	Compressive strength (N/mm^2)
1	10.11.2015	08.12.2015	8.237	471.6	20.96
2	10.11.2015	08.12.2015	8.365	503.2	22.36
3	10.11.2015	08.12.2015	8.219	489.7	21.76

*Information is furnished by the Customer/Representative.

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

****

VISHWANATH .C
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಶೆಟ್ಟಿಹಳ್ಳಿ ಉಪವಿಭಾಗ, ದಾಸರಹಳ್ಳಿ ವಲಯ
ಬೃಹತ್ ಬೆಂಗಳೂರು ಮಹಾನಗರ ಪಾಲಿಕೆ
ಎಸ್.ಎಂ ರಸ್ತೆ, ರವೀಂದ್ರನಗರ, ಬೆಂಗಳೂರು

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagar, Bangalore-79.
Tele Fax : 23223227, Website : www.civiltechconsultants.com
E-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com